


Calcium Fluoride (CaF_2)

Custom sizes and specifications are available

Crystal Structure: Monocrystalline, Polycrystalline **Types Available:** IR Grade, UV Grade, Excimer Grade

CRYSTALLOGRAPHIC		MECHANICAL	
Syngony	Cubic	Density, g/cm ³ at 20 deg C	3.18
Symmetry Class	m3m	Mohs Hardness	4
Lattice Constants, Angstrom	a = 5.462	Vickers Microhardness, Pa	165×10^7
	c=a	Constants of Elastic Compliance, Pa ⁻¹	$S_{11}=6.83 \times 10^{-12}$ $S_{12}=-1.53 \times 10^{-12}$ $S_{44}=29.58 \times 10^{-12}$
Cleavability	<111>, perfect	Young Modulus ϵ , Pa	
Orientation	<111>, <100>	in <100> direction	14.61×10^{10}
OPTICAL		in <111> direction	8.99×10^{10}
Refractive Index at n _e	1.4349	Shear Modulus (G), Pa	
Refractive Index n _F - n _C	0.0043	in <100> direction	4.76×10^{10}
Refractive Index at n _{10.6}	1.2996	in <111> direction	3.38×10^{10}
Thermal Coefficient of Refractive Index at 3.39 microns for +/- 60 deg C	(-0.95)... (-1.17) $\times 10^{-5}$	Poisson Ratio	0.216
Transmission Range, Microns	0.15 - 9.0	CHEMICAL	
THERMAL		Molecular Weight	78.08
Thermal Linear Expansion, deg C ⁻¹ for +/- 60 deg C	(16.5...19.4) $\times 10^{-6}$	Solubility	
Thermal Conductivity, W/(m * deg C) at 36 deg C	9.71	in water, gram/100cm ³	0.0016
Specific Heat Capacity, J/(kg * deg C)	0.8876×10^3	*IR Grade is the most commonly used grade in ISP Optics Catalog, however ISP Optics reserves the right to use any grade at its discretion.	
Thermal Stability, deg C	20 +/-2		
Melting Point, deg C	1418		

Transmittance $\tau(\lambda)$ vs. Wavelength λ



Refr. Index n vs. Wavelength λ		Internal Transmittance Ti(λ) vs. Wavelength λ	
WAVELENGTH, MICRONS	REFRACTIVE INDEX	WAVELENGTH, MICRONS	INTERNAL TRANSMITTANCE
0.2	1.4951	0.35	0.97
0.5	1.4951	0.5	0.97
1.0	1.4951	1.0	0.99
2.0	1.4951	3.0	0.99
3.0	1.4951	5.0	0.99
4.0	1.4951	6.0	0.98
5.0	1.4951	7.0	0.97
6.0	1.4951	8.0	0.88
7.0	1.4951	9.0	0.59
8.0	1.4951	10.0	0.19
9.0	1.4951		
10.0	1.4951		
11.0	1.4951		
12.0	1.4951		

For Reference Only

ISP Optics Corp:
2603 Challenger Tech Court, Suite 100
Orlando, FL 32826
Tel: +800-909-4207
www.ispoptics.com

ISP Optics Latvia:
24a Ganibu Dambis, korp 13
Riga, LV-1005, Latvia
T: +371 67 323 779
sales@ispoptics.eu

