

Germanium (Ge)

Custom sizes and specifications are available

CRYSTALLOGRAPHIC

Syngony	Cubic
Symmetry Class	m3m
Lattice Constants, Angstrom	a=5.657 c=a
Cleavability	(111), perfect

OPTICAL

Refractive Index at $n_{10.6}$	4.0034
Refractive Index $n_{8.0} - n_{12.5}$	0.0036
Thermal Coefficient of Refractive Index at 3.39 microns for +/- 60 deg C	$35-40 \times 10^{-5}$
Transmission Range, Microns	2-17

THERMAL

Thermal Linear Expansion, deg C ⁻¹ for +/- 60 deg C	$(5.1...5.8) \times 10^{-6}$
Thermal Conductivity, W/(m•deg C) at 27 deg C	59.8
Specific Heat Capacity, J/(kg•deg C)	0.310
Melting Point, deg C	937
Absorbance μ (λ), cm ⁻¹ at 10.6 microns	0.027

MECHANICAL

Density, g/cm ³ at 20 deg C	4.83
Mohs Hardness	3
Vickers Microhardness, Pa	82×10^7

Young Modulus E , Pa

in <100> direction	10.32×10^{10}
in <111> direction	15.56×10^{10}

Shear Modulus (G), Pa

in <100> direction	6.72×10^{10}
in <111> direction	4.67×10^{10}

Poisson Ratio

0.278

CHEMICAL

Molecular Weight	72.61
Solubility	insoluble
in water, gram/100cm ³	


Refr. Index n vs. Wavelength λ

WAVELENGTH, MICRONS	REFRACTIVE INDEX
2.0	4.1079
3.0	4.0446
4.0	4.0242
5.0	4.0153
6.0	4.0106
7.0	4.0076
8.0	4.0053
9.0	4.0047
10.0	4.0040
11.0	4.0031
12.0	4.0029
12.5	4.0024
15.0	4.0017

Internal Transmittance T_i (λ) vs. Wavelength λ

WAVELENGTH, MICRONS	INTERNAL TRANSMITTANCE
3.0	0.97
5.0	0.97
6.0	0.97
7.0	0.97
8.0	0.97
9.0	0.97
10.0	0.96
12.0	0.70
15.0	0.56

Transmittance τ (λ) vs. Wavelength λ



For Reference Only

ISP Optics Corp:

2603 Challenger Tech Court, Suite 100
Orlando, FL 32826
Tel: +800-909-4207

www.ispoptics.com

ISP Optics Latvia:

24a Ganibu Dambis, korp 13
Riga, LV-1005, Latvia
T: +371 67 323 779

sales@ispoptics.eu



A LightPath COMPANY